

TEST REPORT

CLIENT SuZhou Tuntex Fiber & Carpet Company

TEST METHOD CONDUCTED

ASTM D7570 (Edge Curl) Standard Test Method for Evaluating

Dimensional Stability of Pile Yarn Floor Covering



DESCRIPTION OF TEST SAMPLE			
IDENTIFICATION	Nylon Carpet Tiles with LuxCushion		
CONSTRUCTION	Multi-Level Loop Pile		
BACKING	LuxCushion (High Density Nylon)		

GENERAL PRINCIPLE

This test is designed to examine dimensional changes in textile floor coverings due to various conditions of heat and moisture. Measurements are taken in the length and cross directions of the test sample after each treatment. A change in the dimension of the test sample is calculated as a percentage of the original preconditioned sample measurement. Shrinkage is indicated by a negative quotation while expansion is indicated by a positive quotation.

TEST RESULTS

	Percent Change		Percent Change	Edge Curl*
Mo		C ₀		0.08 Inch
M _{T1}	+0.077%	Ctı	+0.018%	0.04 Inch
M _{T2}	+0.124%	C _{T2}	+0.069%	0.00 Inch
M _{T3}	+0.097%	C ₁₃	+0.091%	0.03 Inch
M _{T4}	+0.094%	C _{T4}	+0.094%	0.03 Inch

*At the client's request, planar change was measured during each stage

M₀ Original measurement in machine direction

C₀ Original measurement in cross direction

T₁ Two hours in drying oven at 60° C

T₂ Two hours submerged in 0.1% detergent solution at 20°C

T₃ Twenty four hours in drying oven at 60°C

T₄ Forty eight hours conditioning at 20°C and 65% relative humidity

Lang aflury

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us